



| | | | | |
|--|----------------------------------|-----------|--|--|
| Brand Name | A-COPPER 11 | | | |
| Material Code | | | | |
| Abbreviation | SNCA / SNCB / RNCA / RNCB | | | |
| Chemical Composition (mass components) in %. Average values of alloy components | | | | |
| Cu | Ni | Mn | | |
| Balance | 3 | 2 | | |

Features and Application Notes

A-COPPER 11 is used as negative leg for the compensating lead for thermocouple types Pt10Rh-Pt and Pt13Rh-Pt. A-COPPER 11 is standardized in the temperature range between 0 and +200 °C.

Form of Delivery

A-COPPER 11 is supplied in the form of wires with dimensions from 0.05 to 13.50 mm Ø in bare condition. Enamelled wires are available in dimensions between 0.05 and 1.50 mm Ø. A-COPPER 11 can also be supplied in form of stranded wire, ribbon, flat wire and rods. Please contact us for the range of dimensions.

Thermoelectrical¹⁾ and Electrical Values in Soft-Annealed Condition

| EMF versus Cu/NIST 175 at +100 °C / mV ²⁾ | EMF versus Pt67/NIST 175 at +100 °C / mV ³⁾ | EMF versus Cu at +200 °C / mV ³⁾ | EMF versus Pt67/NIST 175 at +200 °C / mV ³⁾ | Electrical resistivity in $\mu\Omega \times \text{cm}$ at +20 °C |
|--|--|---|--|--|
| -0.646 / -0.647 | 0.127 / 0.126 | -1.441 / -1.469 | 0.396 / 0.368 | 12.000 |
| SC/RC | SC/RC | SC/RC | SC/RC | |

Physical Characteristics (Reference Values)

| Density at +20 °C | Melting point | Specific heat at +20 °C | Thermal conductivity at +20 °C | Average linear thermal expansion coefficient between +20 °C and +100 °C | Magnetic at room temperature |
|-------------------------|---------------|-------------------------|--------------------------------|---|------------------------------|
| g/cm³ | °C | J/g K | W/m K | 10⁻⁶/K | |
| 8.90 | +1,080 | 0.38 | around 200.00 | 18.00 | no |

Mechanical Properties at +20 °C in Annealed Condition³⁾

| | Tensile strength MPa | Elongation % | Hardness HV10 |
|-------------|----------------------|--------------|-----------------|
| hard | > 500 | 2 | > 170 |
| soft | 320 | 33 | 90 |

Notes on Treatment // A-COPPER 11 is easy to process. The alloy can be soldered and brazed without difficulty. All known welding methods are applicable.

1) The exact EMF values can be calculated with a "EMF-Software", which can be downloaded from our homepage.

2) Reference at 0 °C.

3) The mechanical values considerably depend on dimension. The indicated values refer to a dimension of 1.0 mm diameter.